Advances in Battery Engineering, Interface Design, and Characterization Mini-Symposium
Room 319 - Session BT2+AS+CA+TF-ThM

Advanced Battery Electrodes

Moderators: Alexander Kozen, University of Vermont, **Tanguy Terlier**, Rice University, **Andrew Westover**, Oak Ridge National Laboratory

11:00am **BT2+AS+CA+TF-ThM-13 Understanding the Electrically-Limited Reaction Kinetics and Dynamics for Conversion Electrode Iron Fluoride**, *Chuan-Fu Lin,* ***Binh Hoang,*** Catholic University of America **INVITED**

To maintain efficient reaction kinetics in standard electrodes, fast and stable ionic and electronic conductive networks are required for long-term reversibility, and this poses the major challenges for conversion-type electrode materials. The phase separation reaction, CM + Li^+ + e^- -> M (reduced metal) + LiX (Li compounds), induced by the lithiation process deteriorates the structural integrity, which certainly destroys the original ionic and electronic pathways and reconstructs new ones. However, it is still unclear whether the transports of conversion electrode are benefited or hindered from the reconstruction of transport pathways due to phase separation, yet the dynamic evolution of electrical conductivity in these systems remains overlooked.

This work aims to investigate the electrically-limited reaction of conversion electrodes upon phase separation and recombination by studying the structural, electrical, and electrochemical properties of amorphous and crystalline iron (III) fluoride (FeF_x) thin films synthesized via sputtering deposition. Using a binder-free lateral device architecture and probing measurement, we dynamically mapped resistivity evolution during electrochemical cycling. While pristine crystalline films exhibit lower initial resistivity than amorphous films, deep lithiation triggers a dramatic drop in resistivity by over five orders of magnitude in both structural variants. Despite the massive volume fraction of the insulating LiF byproduct (1 : 4.17 for Fe : LiF ratio), the resistivity reduced to ~0.35 Ω·m, demonstrating a common conduction pathway formed by a metallic Fe network within the nanocomposite. Correlating this resistivity evolution with X-ray Photoelectron Spectroscopy (XPS) spectra reveals the electrically-controlled reaction dynamics of the thin-film conversion electrodes. Conversely, delithiation results in a resistivity increase of two orders of magnitude, driven by a rate-dependent electrochemical "trapping effect." Fast charging causes isolated Fe domains electronically stranded within the LiF matrix and driving irreversible capacity loss. These results elucidate the coupling between chemical quantifications, reaction dynamics, and electrical properties, providing understanding of the influence of the electrical conductivity for high-energy-density conversion cathodes.

11:30am **BT2+AS+CA+TF-ThM-15 Molecular Mapping Investigations of Prelithiation Alloy Formation via Thermal Evaporation on Silicon Based Electrodes**, ***Gabriel Parker,*** *Amanda Musgrove, Gabriel Veith, Ivan Matyushov, Xiao-Ying Yu,* Oak Ridge National Laboratory, USA

Abstract: Silicon based composites have become increasingly popular as potential anodes for lithium-ion batteries due to their large storage capacity, relative abundance, and low cost. However, these anodes often see reduced initial columbic efficiency (ICE) due to disruptive volume expansion up to 300% and continuous unstable solid electrolyte interphase (SEI) layer formation. Prelithiation, the process of adding excess reservoir of Li to the electrode to compensate for irreversible SEI formation losses during their sample preparation, has proven to solve the issue of immediate capacity loss. Thermal evaporation is a prelithiation technique with limited studies on its effectiveness. In this study, time-of-flight secondary ion mass spectrometry (ToF-SIMS) is used to investigate the benefits of prelithiation via thermal evaporation. ToF-SIMS provides chemical mapping and spatial information in 2D and 3D visualizing the deposition of lithium, identifying Li_xSi_y alloy and $Li_xSi_yO_z$ silicate formation, and the distribution of lithium passivation into the electrodes. Passivation under different atmospheric conditions, such as inert Argon (Ar) and Ar/carbon dioxide (CO_2), highlights the impact of the environment on the passivation effectiveness and formation of Li_xSi_y alloy and $Li_xSi_yO_z$ silicate. The ToF-SIMS molecular imaging and depth profiling results indicate that prelithiation via thermal evaporation effectively distributes lithium throughout the depth profile thickness of several hundred nanometers. It induces a greater degree of $Li_xSi_yO_z$ silicate formation over Li_xSi_y alloy. The results provided by the ToF-SIMS are corroborated by electrochemical measurement of the electrodes under inert Ar and Ar/CO_2 environments indicating that the Ar/CO_2 electrode retained a higher specific capacity over multiple cycles. Our ToF-SIMS characterization results show the effectiveness of thermal evaporation in producing a more stable electrode and an electrode with an effective lithium reserve that can preserve its capacity.

Keywords: Solid-state batteries, solid-electrolyte interface, ToF-SIMS, prelithiation, molecular imaging.

Author Index

Bold page numbers indicate presenter

— H —

Hoang, Binh: BT2+AS+CA+TF-ThM-13, **1**

— L —

Lin, Chuan-Fu: BT2+AS+CA+TF-ThM-13, 1

— M —

Matyushov, Ivan: BT2+AS+CA+TF-ThM-15, 1

Musgrove, Amanda: BT2+AS+CA+TF-ThM-15, 1

— P —

Parker, Gabriel: BT2+AS+CA+TF-ThM-15, **1**

— V —

Veith, Gabriel: BT2+AS+CA+TF-ThM-15, 1

— Y —

Yu, Xiao-Ying: BT2+AS+CA+TF-ThM-15, 1